

## PRIMER-T®

## Single Component, Non Staining Primer for Non Porous Substrates

#### DESCRIPTION

PRIMER-T<sup>®</sup> is one component, colorless, non-staining primer especially designed to secure the adhesion of Hyperdesmo-T<sup>®</sup> on non-porous substrates. Although designed for Hyperdesmo -T, it is fully suited for all products in the Hyperdesmo product range.

Chemically, **PRIMER-T**<sup>®</sup> is a composed of a moisture reacting organosilane in a mixture of solvents and additives to ensure overall wetting of the substrate.

**PRIMER-T**<sup>®</sup> is easily applied by wetting a clean cloth and essentially cleaning the surface to be protected with **Hyperdesmo –T.** 

**PRIMER-T**<sup>®</sup> dries quickly, within 10-15 max. the surface is ready for application.

#### RECOMMENDED FOR

Priming of non-porous substrates.

- Glassy tiles
- glass
- · Slightly porous marble

#### LIMITATIONS

- · Apply minimal amount of primer by cloth
- · Avoid pools, runs, and drips.

#### FEATURES & BENEFITS

- Quick drying.
- No thinning is required
- Non-Staining.
- Easy application

#### SURFACE PREPARATION

Clean the surface, using jet water if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, curing membranes must be removed. Fill surface irregularities with adequate products.

Apply the material with cloth as cleaning the surface. Allow10-15 min for drying and subsequently apply Hyperdesmo-T.

#### PRECAUTIONS

PRIMER-T® contains volatile flammable Solvents. Apply in well-ventilated areas. Don't smoke. Apply far away from naked flames. In closed areas use force ventilation and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor.

Ask for MSDS (Material Safety Data Sheet)

#### CONSUMPTION

#### **Minimum Total Consumption:**

#### **PACKAGING**

20Lt, 5lt, 1lt

#### SHELF LIFE

**PRIMER-T**<sup>®</sup> can be kept for minimum 12 months in the original unopened pails at a temperature of 5 °C - 25 °C in dry places.

None of our instructions and specifications in writing is binding in general and with respect to any third parties protective rights in particular, or do they relieve you of your duty to subject our products to an adequate examination with regard to their suitability.

Certified quality, environmental and occupational health & safety management systems: ISO 9001/14001 & OHSAS 18001.



Page 2/2

# PRIMER-T®

## TECHNICAL SPECIFICATIONS OF PRIMER-T

### **The Liquid product:**

PROPERTY	UNITS	METHOD	SPECIFICATION
-Viscosity (BROOKFIELD)	cР	ASTM D2196-86, at 25°C	40
- Specific weight	gr/cm <sup>3</sup>	ASTM D1475 / DIN 53217 / ISO 2811,	0.83
		at 20°C	
-Flash point	°C	ASTM D93, Closed cup	42
-Dry time	min	-	10-15
at 77deg F (25°C) & 55% RH			

