

## HYPERDESMO®-PARTICULAR

### One-component, polyurethane membrane used for roof-details waterproofing

#### DESCRIPTION

**HYPERDESMO®-PARTICULAR** is a thixotropic and fiber-reinforced, one component polyurethane liquid membrane used for waterproofing and protection of roof detail structures.

Due to its unique formulation, it cures rapidly to form a bubble free thick layer membrane with excellent mechanical properties. This product is ideal for use during the winter months or in climates with relatively low humidity.

Apply with brush or roller. Minimum consumption:  $\pm 1.8 \text{ kg/m}^2$ .

#### COMPLIANCE

The product complies with the EU guideline for this type of materials, EOTA (European Organization of Technical Approval).

#### RECOMMENDED FOR

Waterproofing and protection of:

- flashings
- wall-floor connections
- chimneys
- pipes
- photovoltaic systems
- air-condition units
- gutters

#### FEATURES & BENEFITS

- No reinforcement necessary in flashing points
- Fast curing! Skin formation time of 2 hours.
- Bubble and defect free membrane.
- Excellent weather and UV resistance.

- Excellent thermal resistance, the product never turns soft. Recommended service temperature 80 °C, max shock temperature 200 °C.
- Resistance in the cold: The film remains elastic even down to -40 °C.
- Excellent mechanical properties, high tensile and tear strength, high abrasion resistance.
- Good chemical resistance.

#### APPLICATION PREREQUISITES

##### Can be successfully applied on:

Concrete, fibrous cement, mosaic, cement roof tiles, old (but well adhered) acrylic and asphalt coats, wood. For information about other substrates, please contact our tech department.

##### Concrete substrate conditions (standard):

- Hardness:  $R_{28} = 15 \text{ Mpa}$ .
- Humidity:  $W < 10\%$ .
- Temperature: 5-35 °C.
- Relative humidity:  $< 85\%$ .

#### APPLICATION PROCEDURE

Clean the surface using a high pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must be removed. Fill surface irregularities with the necessary product.

#### CONSUMPTION

Minimum total consumption:  $\pm 1,8 \text{ kg/m}^2$ .

#### CLEANING

Clean tools and equipment first with paper towels and then using SOLVENT-01. Rollers will not be

## HYPERDESMO<sup>®</sup> - PARTICULAR

re-usable.

### PACKAGING

1 kg, 5 kg

### SHELF LIFE

Can be kept for minimum 12 months in the original unopened pails in dry places and at temperatures of 5-25 °C. Once a pail has been opened, use as soon as possible.

### PRECAUTIONS

Contains volatile flammable solvents. Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor. The MSDS (Material Safety Data Sheet) is available on request.

### TECHNICAL SPECIFICATIONS

**In liquid form (before application):**

PROPERTY	UNITS	METHOD	SPECIFICATION
Viscosity (BROOKFIELD)	cP	ASTM D2196-86, @ 25 °C	5000-7000
Specific weight	gr/cm <sup>3</sup>	ASTM D1475 / DIN 53217 / ISO 2811, @ 20°C	1.4-1.5
Flash point	°C	ASTM D93, closed cup	42
Tack free time, @ 77 °F (25 °C) & 55% RH	hours	-	2-3
Recoat time	hours	-	6-48

**The cured membrane:**

PROPERTY	UNITS	METHOD	SPECIFICATION
Service temperature	°C	-	-40 to 80
Max. temperature short time (shock)	°C	-	200
Hardness	Shore A	ASTM D2240 / DIN 53505 / ISO R868	70
Tensile strength at break @ 23 °C	Kg/cm <sup>2</sup> (N/mm <sup>2</sup> )	ASTM D412 / EN-ISO-527-3	80 (8,5)
Percent elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 200
QUV Accelerated Weathering Test (4hr UV, @ 60 °C (UVB-Lamps) & 4hr COND @ 50	-	ASTM G53	passed (2,000 hours)

# HYPERDESMO<sup>®</sup> - PARTICULAR

°C)			
-----	--	--	--

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

